



COLD FORCE® TECHNICAL DATA SHEET

			CF. 140 14 Micron	CF. 160 16 Micron	CF. 180 18 Micron	CF. 203 20.3 Micron	CF. 255 25.5 Micron	CF. 305 30.5 Micron
Thickness	ASTM D-4649	Gauge	55	63	71	80	100	120
Puncture Force	ASTM D-5748	Pounds	3	3.6	4.3	5	6.4	7.8
Tensile Ultimate MD	ASTM D-882	PSI	2682	3268	3339	3446	3480	3505
Tensile Ultimate CD	ASTM D-882	PSI	2457	2477	2480	2510	2515	2526
Tensile Yield MD	ASTM D-882	PSI	1294	1325	1333	1396	1400	1411
Tensile Yield CD	ASTM D-882	PSI	1125	1205	1206	2510	1230	1232
Elongation at MD	ASTM D-882	%	375	405	429	462	490	510
Elongation at CD	ASTM D-882	%	427	468	482	488	540	625
Unstretched Cling	ASTM D-4649	Grams (g)/in	211	218	253	258	262	273

All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.