



GLOBAL FORCE® TECHNICAL DATA SHEET

			GF.127 12.7 Micron	GF. 153 15.3 Micron	GF. 178 17.8 Micron	GF. 190 19 Micron	GF. 203 20.3 Micron	GF. 229 22.9 Micron	GF. 255 25.5 Micron	GF. 260 26 Micron	GF. 280 28 Micron	GF. 292 29.2 Micron	GF. 305 30.5 Micron	GF. 380 38 Micron
Thickness	ASTM D-4649	Gauge	50	60	70	75	80	90	100	102	110	115	120	150
Puncture Force	ASTM D-5748	Pounds	4.7	5.2	5.8	6.4	6.7	7	7.3	7.4	7.6	7.9	8.2	8.8
Tensile Ultimate MD	ASTM D-882	PSI	4335	4625	4775	5095	5170	5300	5475	5475	5600	5600	5625	5725
Tensile Ultimate CD	ASTM D-882	PSI	2750	2825	2920	2980	3000	3020	3030	3030	3045	3150	3200	3500
Tensile Yield MD	ASTM D-882	PSI	1375	1400	1425	1445	1455	1468	1480	1480	1500	1505	1515	1610
Tensile Yield CD	ASTM D-882	PSI	1281	1295	1310	1322	1330	1340	1345	1345	1352	1360	1367	1380
Elongation at MD	ASTM D-882	%	420	450	464	499	510	518	520	520	540	540	550	575
Elongation at CD	ASTM D-882	%	495	518	530	550	560	570	579	579	585	589	605	620
Unstretched Cling	ASTM D-4649	Grams (g)/in	175	177	179	180	181	181	182	182	182	184	185	189

All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.