



## CONTRAST<sup>®</sup> TECHNICAL DATA SHEET

			<b>12.7 Micron</b>	<b>17.8 Micron</b>	<b>22.9 Micron</b>
Thickness	ASTM D-4649	Gauge	50	70	90
Puncture Force	ASTM D-5748	Pounds	5.1	6.3	7.3
Tensile Ultimate MD	ASTM D-882	PSI	5280	5390	5490
Tensile Ultimate CD	ASTM D-882	PSI	4940	5180	5400
Tensile Yield MD	ASTM D-882	PSI	1280	1365	1440
Tensile Yield CD	ASTM D-882	PSI	1345	1365	1400
Elongation at MD	ASTM D-882	%	440	460	480
Elongation at CD	ASTM D-882	%	610	630	650
Slip	ASTM D-1894	150% Prestretch COF	< 1	< 1	< 1

*All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.*